
Continuously hot rolled low carbon steel sheet and strip for cold forming — Technical delivery conditions

ICS 77.140.50

National foreword

This British Standard is the UK implementation of EN 10111:2008. It supersedes BS EN 10111:1998 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee ISE/10, Flat rolled steels products.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 May 2008

© BSI 2008

ISBN 978 0 580 54793 5

Amendments/corrigenda issued since publication

Date	Comments

English Version

Continuously hot rolled low carbon steel sheet and strip for cold forming - Technical delivery conditions

Tôles et bandes en acier doux laminées à chaud en continu
pour formage à froid - Conditions techniques de livraison

Kontinuierlich warmgewalztes Band und Blech aus weichen
Stählen zum Kaltumformen - Technische Lieferbedingungen

This European Standard was approved by CEN on 29 February 2008.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents		Page
Foreword.....		3
1	Scope	4
2	Normative references.....	4
3	Terms and definitions	4
4	Classification and designation.....	5
4.1	Classification.....	5
4.2	Designation	5
5	Requirements.....	5
5.1	Steelmaking and manufacturing processes	5
5.2	Deoxidation	5
5.3	Chemical composition	5
5.4	Delivery conditions.....	5
5.5	Mechanical properties.....	6
5.6	Surface characteristics	6
5.7	Suitability for surface coating	6
5.8	Weldability.....	7
5.9	Tolerances on dimensions and shape	7
6	Tests.....	9
6.1	General.....	9
6.2	Inspection units	9
6.3	Number of tests.....	9
6.4	Sampling.....	9
6.5	Test methods.....	10
6.6	Retests.....	10
6.7	Inspection document.....	10
7	Marking	10
8	Packing	11
9	Storage and transportation.....	11
10	Disputes.....	11
11	Information to be provided by the purchaser at the time of enquiry and order.....	11
11.1	Mandatory information.....	11
11.2	Options	11
Bibliography.....		12

Foreword

This document (EN 10111:2008) has been prepared by Technical Committee ECISS/TC 13 “Flat products for cold working - Qualities, dimensions, tolerances and specific tests”, the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2008, and conflicting national standards shall be withdrawn at the latest by October 2008.

This document supersedes EN 10111:1998.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European Standard specifies the grades of continuously hot rolled low carbon steel sheet and strip (in coils) for cold forming.

Depending on its actual width, strip is classified as:

hot rolled wide strip if its width is greater than or equal to 600 mm;

hot rolled slit wide strip if its width is less than 600 mm.

For each grade, it specifies the chemical composition and the mechanical properties.

This European Standard is applicable to products of thickness not less than 1,0 mm and not exceeding 11 mm.

This European Standard is not applicable to products covered by other standards, such as:

hot rolled products of non-alloy structural steels for general use (see EN 10025 all parts);

steel sheet for pressure purposes (see EN 10028 all parts);

steel sheet for welded gas cylinders (see EN 10120);

quenched and tempered steels (see EN 10083-1 and EN 10083-2).

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references the latest edition of the referenced document (including any amendments) applies.

EN 10002-1, *Metallic materials — Tensile testing — Part 1: Method of test at ambient temperature*

EN 10021, *General technical delivery requirements for steel products*

EN 10027-1, *Designation systems for steels - Part 1: Steel names*

EN 10027-2, *Designation systems for steels — Part 2: Numerical system*

EN 10051, *Continuously hot-rolled uncoated plate, sheet and strip of non-alloy and alloy steels - Tolerances on dimensions and shape*

EN 10079, *Definition of steel products*

EN 10204, *Metallic products — Types of inspection documents*

EN ISO 14284, *Steel and iron - Sampling and preparation of samples for the determination of chemical composition (ISO 14284:1996)*

3 Terms and definitions

For the purposes of this European Standard, the terms and definitions of hot rolled flat products are those given in EN 10079.

4 Classification and designation

4.1 Classification

The choice of steel grade and product type is left to the purchaser. For this choice, the purchaser may be advised by the manufacturer, but without any liability on the part of the latter, unless agreed at the time of enquiry and order.

Hot rolled products are classified into four grades DD11, DD12, DD13 and DD14 defined by chemical composition, mechanical and forming characteristics (see Table 1).

4.2 Designation

4.2.1 The steel names are in compliance with EN 10027-1; the steel numbers, with EN 10027-2.

4.2.2 Products conforming to this European Standard shall be designated, in order, in the following way:

- a) product designation (e.g. "strip", "sheet" or "slit strip cut longitudinally") in line with EN 10079;
- b) number of this European Standard (EN 10111);
- c) symbolic or numerical designation of the steel (see Table 1).

EXAMPLE Strip EN 10111 – DD13

or

Strip EN 10111 – 1.0335

5 Requirements

5.1 Steelmaking and manufacturing processes

Unless otherwise agreed at the time of enquiry and order, the steelmaking and manufacturing processes are left to the discretion of the manufacturer.

The purchaser shall be informed of these processes if he specifies it.

5.2 Deoxidation

For grade DD11 the method of deoxidation shall be at the manufacturer's discretion. Grades DD12, DD13 and DD14 shall be fully killed.

5.3 Chemical composition

Table 1 gives the permissible chemical composition limits in the cast.

5.4 Delivery conditions

5.4.1 The products shall usually be delivered with their surface as rolled. By agreement at the time of enquiry and order, the products may be delivered with descaled surface. When they are delivered as rolled, they are covered with a thin layer of scale of variable coloration.

The products may be supplied with a light skin-pass, either at the manufacturer's discretion or by agreement at the time of enquiry and order.

5.8 Weldability

The products are suitable for standard welding processes. However, the welding process and possible specific requirements of the resulting welded component should be specified at the time of enquiry and order, e.g. gas welding, structural safety requirements.

For non-descaled products, the welding process shall take into account the presence of a layer of scale.

5.9 Tolerances on dimensions and shape

The tolerances on dimensions and shape are given in EN 10051

Table 1 — Characteristics ^a

Steel name	Steel number	Method of deoxidation	Ladle analysis chemical composition b				Mechanical properties c							Validity
							R_{eL} d		R_m	Minimum elongation after fracture				
			C	Mn	P	S	1,0 mm ≤ e e < 2 mm	2 mm ≤ e e ≤ 11 mm		$L_0 = 80$ mm			$L_0 = 5,65 \sqrt{S_0}$	
										max. %	max. %	max. %		max. %
DD11	1.0332	At the discretion of the manufacturer	0,12	0,60	0,045	0,045	170 to 360	170 to 340	440	22	23	24	28	–
DD12	1.0398	Fully killed	0,10	0,45	0,035	0,035	170 to 340	170 to 320	420	24	25	26	30	6
DD13	1.0335	Fully killed	0,08	0,40	0,030	0,030	170 to 330	170 to 310	400	27	28	29	33	6
DD14	1.0389	Fully killed	0,08	0,35	0,025	0,025	170 to 310	170 to 290	380	30	31	32	36	6

NOTE 1 MPa = 1 N/mm².

- ^a The mechanical characteristics relate only to hot rolled non-descaled or chemically descaled and oiled products, skin-passed or not.
- ^b Unless otherwise agreed at the time of enquiry and order, nitrogen-fixing elements such as titanium and boron may be added at the discretion of the manufacturer.
- ^c As long as the width of the product permits, the test pieces for the tensile tests shall be taken transverse to the direction of rolling.
- ^d $R_{p0,2}$ shall be used instead of R_{eL} if the product does not exhibit any yield phenomenon.
- ^e It is recommended that products in grade DD11 should be formed within 6 weeks from the time of their availability.

6 Tests

6.1 General

6.1.1 The purchaser shall specify at the time of enquiry and order his requirements for:

- type of inspection in accordance with EN 10021;
- type of inspection document for the products in accordance with EN 10204.

6.1.2 Specific inspection and testing shall be carried out in accordance with 6.2 to 6.6.

6.2 Inspection units

The inspection units for products of the same grade and nominal thickness are given in Table 2.

Table 2 — Inspection units

Steel name	Inspection unit t
DD11	150
DD12	100
DD13	60
DD14	40

6.3 Number of tests

A series of tests comprises all the tests necessary to verify the specified characteristics:

- tensile test;
- by agreement at the time of enquiry and order, a product chemical analysis.

6.4 Sampling

For sheets, the selection of the product(s) for testing is left to the discretion of the inspection representative.

For wide strips and slit wide strips, the samples should preferably be taken from the outer end.

For sheets and wide strips, the samples shall be taken so that the axis of the test pieces is at half distance between the edge and the axis of the products.

The test pieces for the tensile tests shall be taken transverse to the direction of rolling unless otherwise agreed at the time of enquiry and order.

6.5 Test methods

6.5.1 Mechanical properties

6.5.1.1 General

The tensile tests shall be carried out in accordance with EN 10002-1.

The lower yield point (R_{eL}) shall be determined to verify the yield strength values indicated in Table 1.

If there are no yield point phenomena, the 0,2 % proof strength ($R_{p0,2}$) shall be determined and shall satisfy the values in Table 1. In cases of dispute, the 0,2 % proof strength value ($R_{p0,2}$) shall be determined.

6.5.1.2 Product thickness less than 3 mm

The test piece used (initial gauge length $L_0 = 80$ mm, width $b = 20$ mm) shall be of type 2 as described in EN 10002-1: the thickness of the test piece is that of the sheet.

6.5.1.3 Product thickness greater than or equal to 3 mm

The test piece used is the proportional test piece with an initial gauge length L_0 given by the following formula:

$$L_0 = 5,65 \sqrt{S_0}$$

where

S_0 is the original cross-sectional area of the parallel length of the test piece; the maximum parallel width is 30 mm and the thickness is that of the sheet.

6.5.2 Chemical composition

For the determination of the chemical composition, EN ISO 14284 and the corresponding European Standards shall apply.

6.6 Retests

The requirements of EN 10021 shall apply. In the case of coils, the retest specimens shall be taken from a distance of at least one lap away, but with a maximum of 20 m from the end of the coil.

6.7 Inspection document

Following agreement at the time of enquiry and order, an inspection document as specified in EN 10204 shall be completed.

7 Marking

When marking is specified, the following information shall be given:

grade designation, in accordance with the designation rules given in clause 4 of this standard;

heat number;

indication of the name or the mark of the supplier.

If the goods are supplied in coils or sheets in bound bundles, the marking may be on a label attached to the coil or bundle.

8 Packing

The packing requirements shall be agreed at the time of enquiry and order.

9 Storage and transportation

Moisture, in particular condensation between the sheets, laps of the coil or other adjacent parts made of hot rolled flat products can lead to the formation of corrosion products. As a precaution, the products should be transported and stored dry and protected from moisture.

10 Disputes

With regard to any claims and actions arising there from, EN 10021 shall apply.

11 Information to be provided by the purchaser at the time of enquiry and order

11.1 Mandatory information

In order to allow the manufacturer to supply products conforming to this European Standard, the following information shall be provided by the purchaser at the time of enquiry and order:

- a) full designation as given in subclause 4.2;
- b) nominal dimensions and ordered quantities;
- c) if inspection documents are required and their type;
- d) any special requirements for packing and marking (e.g. bar coding, see EN 606);
- e) limits on the mass and the sizes of the coils and the individual bundles.

11.2 Options

The following information is optional:

- a) if the products are to be supplied skin-passed;
- b) if the products are to be supplied descaled;
- c) if the products are to be supplied with sheared edges;
- d) if oiling is not required in descaled products;
- e) if the products are to be supplied as suitable for making a specific part;
- f) if an external inspection is to be carried out at the manufacturer's works;
- g) intended application of the products, including surface coating and welding technique.

Bibliography

- [1] EN 606, *Bar coding – Transport and handling labels for steel products*
- [2] EN 10025 (all parts), *Hot rolled products of non-alloy structural steels*
- [3] EN 10028 (all parts), *Flat products made of steels for pressure purposes*
- [4] EN 10083-1, *Steels for quenching and tempering - Part 1: General technical delivery conditions*
- [5] EN 10083-2, *Steels for quenching and tempering - Part 2: Technical delivery conditions for non alloy steels*
- [6] EN 10120, *Steel sheet and strip for welded gas cylinders*

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001. Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager. Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553. Email: copyright@bsi-global.com.

BSI
389 Chiswick High Road
London
W4 4AL

