
Resilient floor coverings — Polyvinyl chloride floor coverings on a filled fibrous backing — Specification

The European Standard EN 13413:2001 has the status of a
British Standard

ICS 97.150

NO COPYING WITHOUT BSI PERMISSION EXCEPT AS PERMITTED BY COPYRIGHT LAW

National foreword

This British Standard is the official English language version of EN 13413:2001.

The UK participation in its preparation was entrusted to Technical Committee PRI/60, Resilient floor coverings, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the BSI Standards Catalogue under the section entitled “International Standards Correspondence Index”, or by using the “Find” facility of the BSI Standards Electronic Catalogue.

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

This British Standard, having been prepared under the direction of the Materials and Chemicals Sector Policy and Strategy Committee, was published under the authority of the Standards Policy and Strategy Committee on 5 March 2002

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 9 and a back cover.

The BSI copyright date displayed in this document indicates when the document was last issued.

Amendments issued since publication

Amd. No.	Date	Comments

ICS 97.150

English version

Resilient floor coverings - Polyvinyl chloride floor coverings on a filled fibrous backing - Specification

Revêtements de sol résilients - Revêtements de sol à base de polychlorure de vinyle sur semelle en fibre minérale -
Spécifications

Elastische Bodenbeläge - Polyvinylchlorid-Bodenbeläge mit einem Rücken aus Fasermaterial - Spezifikationen

This European Standard was approved by CEN on 4 November 2001.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Foreword

This European Standard has been prepared by Technical Committee CEN /TC 134, "Resilient and textile floor coverings", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2002, and conflicting national standards shall be withdrawn at the latest by June 2002.

Annexes A and B are informative.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European Standard specifies the characteristics of floor coverings with compact surface layers, made of polyvinyl chloride and modifications thereof, on a filled fibrous backing and supplied in roll form.

To encourage the consumer to make an informed choice, the standard includes a classification system (see EN 685) based on intensity of use, which shows where these floor coverings should give satisfactory service. It also specifies requirement for marking.

2 Normative References

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 424, Resilient floor coverings — Determination of the effect of simulated movement of a furniture leg.

EN 425, Resilient floor coverings — Determination of the effect of a castor chair.

EN 426, Resilient floor coverings — Determination of width, length, straightness and flatness of sheet material.

EN 428, Resilient floor coverings — Determination of overall thickness.

EN 429, Resilient floor coverings — Determination of the thickness of layers.

EN 430, Resilient floor coverings — Determination of mass per unit area.

EN 432, Resilient floor coverings — Determination of shear force.

EN 433, Resilient floor coverings — Determination of residual indentation after static loading.

EN 434, Resilient floor coverings — Determination of dimensional stability and curling after exposure to heat.

EN 435, Resilient floor coverings — Determination of flexibility.

EN 660-1, Resilient floor coverings — Determination of wear resistance — Part 1: Stuttgart test.

EN 660-2, Resilient floor coverings — Determination of wear resistance — Part 2: Frick-Taber test.

EN 661, Resilient floor coverings — Determination of the spreading of water.

EN 684, Resilient floor coverings — Determination of seam strength.

EN 685, Resilient floor coverings — Classification.

EN 12466, Resilient floor coverings — Vocabulary.

EN ISO 105-B02, Textiles — Tests for colour fastness — Part B02: Colour fastness to artificial light: Xenon arc fading lamp test (ISO 105-B02:1994, including Amendment 1:1998).

3 Terms and definitions

For the purposes of this European Standard, the terms and definitions of EN 12466 and the following terms and definitions apply:

3.1

filled fibrous backing

a backing made in a wet process, predominantly from mineral fillers, as well as synthetic and natural fibres (non-asbestos formulated), binders, and which is suitable for use as a support for floor covering

3.2

polyvinyl chloride floor covering on a filled fibrous backing

floor covering consisting of polyvinyl chloride surface layer applied to a filled fibrous backing

4 Requirements

4.1 General requirements

Polyvinyl chloride floor coverings described in this standard shall conform with the appropriate general requirements specified in Table 1, when tested in accordance with the methods given therein.

4.2 Classification Requirements

4.2.1 Wear group classification

Floor coverings described in this standard shall be classified in the appropriate wear group specified in Table 2, i.e. in group T, P, M, when tested in accordance with EN 660-1 or EN 660-2.

NOTE The tests are intended to determine the wear resistance of wear layers defined either by thickness loss (EN 660-1) or volume loss (EN 660-2).

Floor coverings with a transparent wear layer are a priori group T and need not be tested.

4.2.2 Level of use classification

Floor coverings described in this standard shall be classified as suitable for different levels of use in accordance with the performance requirements specified in Table 3, when tested with the methods given therein. Classification shall conform to the scheme established in EN 685.

Table 1 – General Requirements

Property	Requirements	Test Method
length width	m mm	not less than the nominal value not less than the nominal value
Overall thickness	mm	EN 426
Average	Nominal value + 0,18 - 0,15	EN 428
Individual results	Nominal value $\pm 0,20$	
Total mass per unit area (average)	g/m ² Nominal value +13 % - 10 %	EN 430
Residual indentation (average)	mm Average value 0,2	EN 433
Dimensional stability	% 0,4	EN 434
Curling after exposure to heat ¹⁾	mm 8	
Colour fastness to artificial light	6 minimum	²⁾ EN ISO 105-BO2 : Method 3
Shear force of backing	N Average 360	EN 432
Spreading of water	No individual value < 280 Time for water to spread to one edge of test piece 16 h	EN 661
Flexibility	Test using a 20 mm mandrel. For products that show signs of cracking, perform a further test using a 40 mm mandrel. If results show no further cracking record the use of a 40 mm diameter mandrel	EN 435 Method A
¹⁾ The test needs only to be carried out for products which are to be laid unbonded to the subfloor. The test needs not be carried out for fully bonded materials. ²⁾ Expose a full size test sample. Store a further test sample in the dark, which will constitute the reference standard for the assessment of colour change.		

Table 2 – Classification requirements for wear groups

Property	Wear class				Test method
	T	P	M	F	
Thickness loss l mm	0,08 ¹⁾	0,08 < l 0,15	0,15 < l 0,30	0,30 < l 0,60	EN 660-1
Volume loss F _v mm ³	F _v 2,0 ¹⁾	2,0 < F _v 4,0	4,0 < F _v 7,5	7,5 < F _v 15,0	EN 660-2
¹⁾ If tested for verification					

Annex A **(informative)**

Optional properties

Where the following properties are required for specific applications, the floor covering should be tested in accordance with the appropriate methods.

- electrical resistance (EN 1081);
- electrostatic propensity (EN 1815);
- effect of stains (EN 423);
- heavy swivel castor (EN 1818).

Annex B (informative)

Additional methods of test

The following test methods are also available for this type of products but do not form part of the specification:

- curling on exposure to moisture (EN 662);
- conventional pattern depth (EN 663);
- volatile loss (EN 664);
- exudation of plasticisers (EN 665);
- gelling (EN 666);
- mass/unit area of a reinforcement backing (EN 718);
- determination of peel resistance (EN 431).

Bibliography

- EN 423, Resilient floor coverings — Determination of resistance to staining.
- EN 431, Resilient floor coverings — Determination of peel resistance.
- EN 662, Resilient floor coverings — Determination of curling on exposure to moisture.
- EN 663, Resilient floor coverings — Determination of conventional pattern depth.
- EN 664, Resilient floor coverings — Determination of volatile loss.
- EN 665, Resilient floor coverings — Determination of exudation of plasticizers.
- EN 666, Resilient floor coverings — Determination of gelling.
- EN 718, Resilient floor coverings — Determination of mass per unit area of a reinforcement or a backing of polyvinyl chloride floor coverings.
- EN 1081, Resilient floor coverings — Determination of electrical resistance.
- EN 1815, Resilient and textile floor coverings — Assessment of static electrical propensity.
- EN 1818, Resilient floor coverings — Determination of the effect of loaded heavy duty castors.

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001. Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager. Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553. Email: copyright@bsi-global.com.