

# Methods of test for screed materials —

## Part 8: Determination of bond strength

The European Standard EN 13892-8:2002 has the status of a  
British Standard

ICS 91.100.10





## National foreword

This British Standard is the official English language version of EN 13892-8:2002.

The UK participation in its preparation was entrusted by Technical Committee B/544, Plastering, rendering, dry lining, screeds and in situ floorings, to Subcommittee B/544/6, Screeds and in situ floorings, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this subcommittee can be obtained on request to its secretary.

### Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the BSI Catalogue under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the BSI Electronic Catalogue or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

This British Standard, having been prepared under the direction of the Building and Civil Engineering Sector Policy and Strategy Committee, was published under the authority of the Standards Policy and Strategy Committee on 28 November 2002

### Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 7 and a back cover.

The BSI copyright date displayed in this document indicates when the document was last issued.

### Amendments issued since publication

| Amd. No. | Date | Comments |
|----------|------|----------|
|          |      |          |
|          |      |          |
|          |      |          |
|          |      |          |
|          |      |          |

ICS 91.100.10

English version

## Methods of test for screed materials - Part 8: Determination of bond strength

Méthodes d'essais des matériaux pour chapes - Partie 8:  
Détermination de la force d'adhérence

Prüfverfahren für Estrichmörtel und Estrichmassen - Teil 8:  
Bestimmung der Haftzugfestigkeit

This European Standard was approved by CEN on 9 October 2002.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

---

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

|                                   | page |
|-----------------------------------|------|
| Foreword.....                     | 3    |
| 1 Scope .....                     | 4    |
| 2 Normative references .....      | 4    |
| 3 Principle.....                  | 4    |
| 4 Symbols and abbreviations ..... | 4    |
| 5 Apparatus and material.....     | 4    |
| 6 Procedure .....                 | 5    |
| 7 Expression of results .....     | 6    |
| 8 Test Report .....               | 6    |

## Foreword

This document (EN 13892-8:2002) has been prepared by Technical Committee CEN/TC 303, "Floor screeds and in-situ floorings in buildings", the secretariat of which is held by DIN.

It was prepared by Working Group 2 "Screed materials and floor screeds – Test methods" taking into account the proposals submitted by Working Group 1 "Screed materials and floor screeds – Definitions, properties and requirements".

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2003, and conflicting national standards shall be withdrawn at the latest by May 2003.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

This European Standard specifies a method for determining the bond strength between a screed and a standard substrate for specimens made from cementitious screed-, calcium sulphate screed-, magnesite screed- and synthetic resin screed material.

## 2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 1766:2000, Products and systems for the protection and repair of concrete structures - Test methods - Reference concretes for testing.

EN 13813, Screed material and floor screeds - Screed material - Properties and requirements.

EN 13892-1, Test methods for screed materials – Part 1: Sampling, making and curing specimens for test.

EN 24624:1992, Paints and varnishes — Pull-off test (ISO 4624:1978).

## 3 Principle

The bond strength is determined as the failure tensile stress applied by a direct load perpendicular to the bond area. The bond strength is calculated as the quotient between the failure load and the test area. The test area is defined by coring or cutting through the screed into the substrate.

## 4 Symbols and abbreviations

F is the failure load in N;

A is the test area in mm<sup>2</sup>;

B is the bond strength in N/mm<sup>2</sup>.

## 5 Apparatus and material

**Test specimen**, of minimum dimensions 300 mm x 300 mm x 50 mm, with a reproducible surface texture, made of concrete according to EN 1766 of type MC (040) with maximum aggregate size 10 mm, water/cement ratio 0,40<sup>3</sup>; and cement content 455 kg/m<sup>3</sup>

**Steel Pull-head plates**, of circular cross section with a diameter of (50±0,5) mm or of a square cross section with a side of (50±0,5) mm. And a thickness of at least 20 mm. On the side on which the adhesive is to be applied, the pull head plate shall be clean and flat with a tolerance of 0,1 mm per 50 mm length. It shall be provided with a



means for attaching the pull-off test equipment ensuring normal application of the load on the surface under test, without the occurrence of bending or shear forces on the test area.

**Resin based adhesive**, e.g. epoxy resin or methylmethacrylate resin.

**Core drilling device and barrel** that enable the drilling of a  $(50 \pm 1,0)$  mm cylinder through the screed. The core barrel should have a cutting edge that stands proud of the cylinder by  $(1,5 \pm 0,5)$  mm (to reduce lateral forces being applied on the test area).

**Diamond sawing machine** that enables a cross cut through the screed.

**Pull off test equipment** complying with EN 24624 with a pulling capacity sufficient to cause tensile bond failure of the specimen. The accuracy shall be within  $\pm 2$  % (a capacity of 10 kN is sufficient for most applications). The pull off equipment shall be capable of applying the load according to 3.1 of EN 24624:1992 and shall be provided with a measurement device that displays the exerted force by an analogue or digital system. The measurement device shall retain the reading of maximum force exerted.

## 6 Procedure

Sampling of screed material and preparation and curing of test specimens shall follow the method in EN 13892-1. If a bonding agent is prescribed by the manufacturer, it shall be applied to the surface of the concrete test specimens. The thickness of the screed shall be within the range declared by the manufacturer.

Either the square or the circular pull-head plates shall be used. The square pull-head plates are preferred where the screed is greater than 20mm in thickness.

A minimum of 5 test areas of approximately 50 mm cross section shall be cored or cut through the screed material or the floor screed. The test areas shall be at least 50 mm apart from each other and at least 50 mm away from the edge of the test specimens. The dimensions of each test area shall be measured to the nearest 0,5 mm. The test area shall be calculated and the result recorded.

After storage, test specimens shall be cut or cored using a core drilling machine or a saw, as appropriate. The cutting shall extend through the screed to a depth of more than 5 mm into the substrate. Water cooling should be avoided, especially for calcium sulphate and magnesite screeds. If water cooling is unavoidable, the cutting or coring should be done at least one day before the tensile testing. Damaged specimens shall be rejected.

The pull-head-plates shall be bonded centrally on the test areas with the adhesive, preventing any excess adhesive from bridging the cut around the test areas.

The tensile load shall be applied perpendicular to the test area through the pull-head plates. The load shall be applied without shock and at a uniform rate of  $0,05 \pm 0,01$  N/(mm<sup>2</sup> s). The failure load shall be recorded. Any test shall be rejected where the mode of failure is fracture at the adhesive layer between the pull-head plate and the screed and the achieved value is lower than the designated value.

## 7 Expression of results

The individual bond (B) strength shall be calculated from the following formula:

$$B = \frac{F}{A}$$

The bond strength shall be calculated as the mean value from the 5 individual values to the nearest 0,1 N/mm<sup>2</sup>.

From a visual assessment, the type of failure of the specimen shall be determined. Types of failure are as follows:

- X = Cohesive failure in the concrete substrate
- X/Y = Failure between the substrate and the screed
- Y = Cohesive failure in the screed
- Z = Failure between the adhesive layer and the pull-head plate

If there is a combination of these types of failure, a visual inspection shall be made of the failure face to estimate the percentage of each type of failure, based on the surface area, for example:

X : X/Y : Y = 40 % : 10 % : 50 %.

Where the screed system comprises more than 1 layer of material the location of failure, if occurring between the layers, shall be recorded.

## 8 Test Report

The test report shall include the following information:

- a) number, title and date of issue of this European Standard;
- b) name and address of the laboratory carrying out the tests and name and address of the laboratory preparing the samples (if different);
- c) identification number of the test report;
- d) name and address of the manufacturer or supplier of the product;
- e) name and identification marks or batch number of the product;
- f) date of supply of the product;
- g) method of sampling (by reference to EN 13892-1) and by which organisation;
- h) place, date and time of sampling;
- i) identification of the screed samples, including type, origin and designation of the screed material by reference to the relevant product standard EN 13813;
- j) preparation (mixing, casting) and storage (curing) conditions by reference to EN 13892-1;
- k) date and time of preparing samples for test (i. e. date and time of any mixing, casting, moulding or demoulding procedure, preparation of the substrate, use of the bonding agent, if appropriate);
- l) age of screed material when tested;

- m) density of each individual test sample;
- n) test method used (reference manual or alternative method, if appropriate), and details of test specimens including number, dimensions, mass, etc. if appropriate;
- o) date of test and the identification number of the apparatus or details of the test equipment used, including the make, type and capacity and the calibrations details;
- p) test results (individual values to the nearest  $0,1 \text{ N/mm}^2$ , and corresponding mean value stated to the nearest  $0,1 \text{ N/mm}^2$ );
- q) remarks;
- r) date of test report and signature.

## BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

### Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

### Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001.

Fax: +44 (0)20 8996 7001. Email: [orders@bsi-global.com](mailto:orders@bsi-global.com). Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

### Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: [info@bsi-global.com](mailto:info@bsi-global.com).

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001. Email: [membership@bsi-global.com](mailto:membership@bsi-global.com).

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

### Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager. Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553. Email: [copyright@bsi-global.com](mailto:copyright@bsi-global.com).