
Aluminium and aluminium alloys — Scrap —

Part 3: Wire and cable scrap

The European Standard EN 13920-3:2003 has the status of a
British Standard

ICS 13.030.50; 77.120.10

ICS 13.030.50; 77.120.10

English version

Aluminium and aluminium alloys - Scrap - Part 3: Wire and cable scrap

Aluminium et alliages d'aluminium - Scrap (matières premières pour recyclage) - Partie 3: Scrap de câble et fils

Aluminium und Aluminiumlegierungen - Schrott - Teil 3: Draht- und Kabelschrott

This European Standard was approved by CEN on 28 February 2003.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

	page
Foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions.....	4
4 Ordering information.....	4
5 Requirements.....	5
5.1 General.....	5
5.2 Characteristics.....	5
5.3 Chemical composition.....	5
5.4 Metal yield.....	6
6 Classification procedure, treatment of non-conformities and arbitration.....	6

Foreword

This document (EN 13920-3:2003) has been prepared by Technical Committee CEN /TC 132, "Aluminium and aluminium alloys", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2003, and conflicting national standards shall be withdrawn at the latest by October 2003.

Within its programme of work, Technical Committee CEN/TC 132 has entrusted CEN/TC132/WG 20 "Scrap" to prepare the following standard.

EN 13920 comprises the following parts under the general title "Aluminium and aluminium alloys — Scrap" :

Part 1: General requirements, sampling and tests

Part 2: Unalloyed aluminium scrap

Part 3: Wire and cable scrap

Part 4: Scrap consisting of one single wrought alloy

Part 5: Scrap consisting of two or more wrought alloys of the same series

Part 6: Scrap consisting of two or more wrought alloys

Part 7: Scrap consisting of castings

Part 8: Scrap consisting of non-ferrous materials from shredding processes destined to aluminium separation processes

Part 9: Scrap from aluminium separation processes of non-ferrous shredded materials

Part 10: Scrap consisting of used aluminium beverage cans

Part 11: Scrap consisting of aluminium-copper radiators

Part 12: Turnings consisting of one single alloy

Part 13: Mixed turnings consisting of two or more alloys

Part 14: Scrap from post-consumer aluminium packagings

Part 15: Decoated aluminium scrap from post-consumer aluminium packagings

Part 16: Scrap consisting of skimmings, drosses, spills and metallics

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European Standard specifies characteristics, chemical composition and metal yield of new and old scrap recovered from wire or cable of unalloyed aluminium with a chemical composition not less than 99,5 % aluminium, or of defined aluminium alloys.

Example

New scrap from manufacturing of cables and wires.

Old scrap from used aluminium cables obtained from dismantling of electrical lines.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 1715-1, Aluminium and aluminium alloys — Drawing stock — Part 1: General requirements and technical conditions for inspection and delivery.

prEN 12258-3:2000, Aluminium and aluminium alloys — Terms and definitions — Part 3: Scrap.

EN 13920-1:2003, Aluminium and aluminium alloys — Scrap — Part 1: General requirements, sampling and tests.

3 Terms and definitions

For the purposes of this European Standard, the terms and definitions given in prEN 12258-3:2000 and EN 13920-1:2003 apply.

4 Ordering information

The ordering information shall include:

number of this European Standard (EN 13920-3);

the scrap category (wire and cable scrap) and the indication whether it is unalloyed aluminium or a defined aluminium alloy;

the gross mass of the consignment;

the definition of the beginning and end of the period during which the scrap shall be delivered;

any characteristics deviating from those specified under 5.1, e.g. diameter of wire, foreign material.

The ordering information should include:

information about the origin of the scrap;

any information about size and surface condition of the pieces, whenever meaningful.

5 Requirements

5.1 General

In addition to the requirements specified in EN 13920-1, the requirements given in 5.2, 5.3 and 5.4 shall be met.

If the scrap does not meet all these requirements, the supplier shall notify the deviating characteristics to the purchaser and shall obtain his agreement before shipment.

NOTE Scrap recovered by dismantling of old electric lines often does not meet all these requirements.

5.2 Characteristics

The scrap shall consist of wire with a minimum diameter of 0,8 mm for any individual wire.

The scrap shall be free from attachment devices, steel core wires, coiling spools of any material, bundling material and other components of electric lines other than aluminium cables and wires.

The scrap shall not be coated and shall be free from burned wire, oil, grease, dust, plastics and any other type of foreign material.

If not otherwise agreed, the scrap shall be supplied after having undergone a processing operation for volume reduction, e.g. baling, coiling, chopping or knife shredding.

5.3 Chemical composition

The chemical composition after melting as determined in accordance with EN 13920-1 shall conform to the requirements given in Table 1 or Table 2 or to the composition of alloys as specified in EN 1715-1.

Table 1 — Chemical composition of wire and cable scrap of unalloyed aluminium

Composition in percent (mass fraction)

Si	Fe	Cu	Mn	Mg	Zn	Ti	others each	Al ^a
max.	min.							
0,25	0,40	0,05	0,05	0,05	0,07	0,05	0,03	99,5

a The aluminium content is the difference between 100 % and the total of all the other elements present with values no less than 0,010 % rounded to the second decimal (before the calculation is made).

Table 2 — Chemical composition of wire and cable scrap of aluminium alloys of the 6xxx series

Composition in percent (mass fraction)

Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	others each	others total	Al ^a
max.	max.									
0,6	0,30	0,05	0,05	0,6	0,05	0,07	0,10	0,05	0,15	Remainder

a The aluminium content is the difference between 100 % and the total of all the other elements present with values no less than 0,010 % rounded to the second decimal (before the calculation is made).

5.4 Metal yield

The metal yield of scrap pertaining to this standard as determined in accordance with EN 13920-1 shall be ≥ 95 %.

6 Classification procedure, treatment of non-conformities and arbitration

The classification procedure which includes sampling and tests, the treatment of non-conformities and arbitration shall be in accordance with EN 13920-1 as appropriate.

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001.

Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001. Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager. Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553. Email: copyright@bsi-global.com.