

Derivatives from coal pyrolysis — Coal tar and pitch based binders and related products: road tars — Characteristics and test methods

The European Standard EN 14260:2003 has the status of a
British Standard

ICS 75.140; 93.080.20

National foreword

This British Standard is the official English language version of EN 14260:2003.

The UK participation in its preparation was entrusted to Technical Committee CII/56, Derivatives from coal pyrolysis, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the BSI Catalogue under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the BSI Electronic Catalogue or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 9 and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

Amendments issued since publication

Amd. No.	Date	Comments

This British Standard, was published under the authority of the Standards Policy and Strategy Committee on 31 October 2003

© BSI 31 October 2003

ISBN 0 580 42848 6

ICS 75.140; 93.080.20

English version

**Derivatives from coal pyrolysis - Coal tar and pitch based
binders and related products : road tars - Characteristics and
test methods**

Produits dérivés de la pyrolyse du charbon - Liants à base
de goudron et de brais issus de la houille et produits
connexes: goudrons routiers - Caractéristiques et
méthodes d'essai

Derivate der Kohlenpyrolyse - Bindemittel aus
Steinkohlenteer und Steinkohlenteerpech und verwandte
Produkte: direkt destillierter Teer - Anforderungen und
Prüfverfahren

This European Standard was approved by CEN on 10 July 2003.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

page

Foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions.....	4
4 Classification.....	5
5 Characteristics.....	5
6 Specifications.....	5
7 Sampling.....	5
8 Test methods.....	5
Annex A (informative) Typical values.....	7
Annex B (informative) Warning to use	8
B.1 Composition - Data on components.....	8
B.2 First aid measures	8
B.3 Handling and storage	8
B.4 Disposal considerations	9

Foreword

This document (EN 14260:2003) has been prepared by Technical Committee CEN /TC 317, "Derivatives from coal pyrolysis", the secretariat of which is held by IBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2004, and conflicting national standards shall be withdrawn at the latest by March 2004.

In this European Standard the annexes A and B are informative.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European Standard specifies the methods of test required to determine the characteristics for "road tars" and their warning to use for the industrial purposes.

Depending on the required application and the desired properties of the end product, different grades of road tars are available.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 1426, Bitumen and bituminous binders - Determination of needle penetration

EN 1427, Bitumen and bituminous binders - Determination of softening point - Ring and Ball method

EN 13357, Bitumen and bituminous binders - Determination of the efflux time of petroleum cut-back and fluxed bitumens

prEN 13702-1, Bitumen and bituminous binders - Determination of dynamic viscosity of modified bitumen - Part 1 : Cone and plate viscometer method

prEN 13702-2, Bitumen and bituminous binders - Determination of dynamic viscosity of modified bitumen - Part 2 : Coaxial viscometer method

EN 13847:2001, Coal tar and pitch based binders and related products - Terminology and classification"

EN ISO 2719, Determination of flash point - Pensky-Martens closed cup method (ISO 2719:2002)

EN ISO 3838, Crude petroleum and liquid or solid petroleum products - Determination of density or relative density - Capillary-stoppered pyknometer and graduated bicapillary pyknometer methods (ISO 3838:1983)

ISO 3733, Petroleum Products and bituminous materials - Determination of water - Distillation method

ISO 6257, Carbonaceous materials used in the production of aluminium - Pitch for electrodes - Sampling

NF T 66-029, Liants hydrocarbonés-Goudrons purs - Détermination de la teneur en naphtalène

NF T 66-030, Liants hydrocarbonés- Goudrons purs - Détermination de la teneur en anthracène

BS 76:1974, Specification for Tars for road purposes

3 Terms and definitions

For the purposes of this European Standard, the terms and definitions given in EN 13847:2001 apply.

4 Classification

For the purposes of this European Standard, the classification according to EN 13847:2001 applies.

5 Characteristics

The following characteristics shall be determined:

- a) Water content,
- b) Density;
- c) Efflux time (cannot be used for modified road tars);
- d) Distillation;
- e) Softening point;
- f) Softening point of distillation residue on 300 ° C;
- g) Needle penetration;
- h) Naphthalene fraction content;
- i) Anthracene fraction content;
- j) Flash point (close cup);
- k) Dynamic viscosity curve for modified road tars measured between 80 ° C and 120 ° C at 4 different temperatures with an interval of approximately 10 ° C between each temperature.

6 Specifications

Specifications of the national standards bodies shall be used.

The typical values given in annex A can be used as requirements.

7 Sampling

The ISO 6257 specifies methods for sampling and preparing samples for testing of road binders.

These methods are applicable to all grades of road tars in liquid or solid form, the latter having softening points higher than 30 ° C (determined according to the method EN 1427) in bulk, or in a numbers of containers making up one batch at sites of manufacture, storage or delivery.

8 Test methods

For the determination of the characteristics according to clause 5, the methods listed in Table 1 have to be used.

Table 1 — Test methods

Characteristic	Test methods
Water content	ISO 3733
Density	EN ISO 3838
Efflux time	EN 13357
Distillation	BS 76:1974, appendix D
Softening point	EN 1427
Needle penetration	EN 1426
Naphthalene fraction content	NF T 66-029
Anthracene fraction content	NF T 66-030
Flash point	EN ISO 2719
Dynamic viscosity	prEN 13702-1, prEN 13702-2

Annex A (informative)

Typical values

The typical values in table A.1 can be used as requirements of the road tars.

Table A.1 — Typical values

CHARACTERISTICS	Straight run- and road tar		Modified tar		Composed tar		Tar emulsion
	sdt ^a	cmt ^b	sdt	cmt	sdt	cmt	
Water content (in %)	< 0,3	< 0,3	< 0,3	< 0,3	< 0,3	< 0,3	min. 45
Density at 20 ° C (in kg/dm ³)	> 1,05	> 1,05	> 1,05	> 1,05	> 1,05	> 1,05	> 1,05
Efflux time 10 mm at 40 ° C (in s)	20 to 140		-	-	20 to 140	-	-
Efflux time 10 mm at 50 ° C (in s)	-	20 to 140	30 to 70	-	-	-	-
Distillation till at 300 ° C (in %)	15 to 25	10 to 20	-	-	15 to 25	-	-
Softening point (in ° C)	-	-	-	> 50	40 to 65	50 to 70	-
Softening point of distillation residue at 300 ° C (in ° C)	35 to 55	35 to 55	-	-	35 to 55	-	-
Needle penetration (in 10 ⁻¹ mm)	-	-	-	-	-	20 to 40	-
Naphthalene fraction content (in %)	< 2	< 2	-	-	< 2		-
Anthracene fraction content (in %)	< 4	< 4	-	-	< 4		-
Flash point (in ° C)	-	-	-	> 101	-	> 101	> 101
Dynamic viscosity at 80 ° C (in mPas)	-	-	-	< 60 000	-	-	-
Dynamic viscosity at 120 ° C (in mPas)	-	-	-	> 300			-
a surface dressing tars b hot coated macadam road tars NOTE Straight run – and roads tars for hot coated macadam can also be used in cold applications.							

Annex B (informative)

Warning to use ¹⁾

B.1 Composition - Data on components

Chemical characterization of Road tars

CAS. N° Designation:	Void.
Identification number (s):	Void.
EINECS Number:	Void.
Description:	Complex mixture of polynuclear aromatic and heterocyclic hydrocarbons.
Dangerous components:	Benzo (d,e,f) chrysene < 1 %

B.2 First aid measures

General information:	Instantly remove any clothing soiled by the product.
After inhalation:	Supply fresh air; consult doctor in case of symptoms.
After skin contact:	Instantly wash with water and soap and rinse thoroughly. After contact with the hot product, cool rapidly with cold water. Do not pull solidified product away from the skin, seek medical treatment.
After eye contact:	Rinse opened eye for several minutes under running water.
After swallowing:	In case of persistent symptoms consult doctor.

B.3 Handling and storage

Handling.

Information for safe handling: Thorough dedusting, ensure good ventilation, exhaustion and the workplace.

Open and handle container with care.

Information about protection against explosions and fires: Keep breathing equipment ready.

Fumes can combine with air to form an explosive mixture.

Storage

Requirements to be met by storerooms and containers: Only stored in heated containers.

Information about storage in one common storage facility: Not required.

Further information about storage conditions: Keep container tightly sealed.

1) The latest edition of the publication of the Material Safety Data Sheet of the product applies

B.4 Disposal considerations

European waste catalogue : The waste code classification is to be carried out according to the European Waste Catalogue (EWC) specifically for each branch of industry and each type of process.

Uncleaned packagings: Disposal must be made according to official regulations.

Must not be disposed of together with household garbage.

Recommendation: Disposal must be made according to official regulations.

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001. Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager. Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553. Email: copyright@bsi-global.com.