

Welding consumables — Wire electrodes, strip electrodes, wires and rods for fusion welding of stainless and heat resisting steels — Classification

The European Standard EN ISO 14343:2007 has the status of a
British Standard

ICS 25.160.20

National foreword

This British Standard was published by BSI. It is the UK implementation of EN ISO 14343:2007. It is identical with ISO 14343:2002, incorporating amendment 1, March 2006. It supersedes BS EN 12072:2000 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee WEE/39, Welding consumables.

A list of organizations represented on WEE/39 can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 March 2007

© BSI 2007

ISBN 978 0 580 50375 7

Amendments issued since publication

Amd. No.	Date	Comments

English Version

**Welding consumables - Wire electrodes, strip electrodes, wires
and rods for fusion welding of stainless and heat resisting steels
- Classification (ISO 14343:2002 and ISO
14343:2002/Amd1:2006)**

Produits consommables pour le soudage - Fils-électrodes,
fils d'apport et baguettes d'apport pour le soudage à l'arc
des aciers inoxydables et des aciers résistant aux
températures élevées - Classification (ISO 14343:2002 et
ISO 14343:2002/Amd1:2006)

Schweißzusätze - Drahtelektroden, Bandelektroden, Drähte
und Stäbe zum Schmelzschiessen von nichtrostenden und
hitzebeständigen Stählen - Einteilung (ISO 14343:2002 und
ISO 14343:2002/Amd1:2006)

This European Standard was approved by CEN on 21 January 2007.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Foreword

The text of ISO 14343:2002 and ISO 14343:2002/Amd1:2006 have been prepared by Technical Committee IIW “International Institute of Welding” of the International Organization for Standardization (ISO) and has been taken over as EN ISO 14343:2007 by Technical Committee CEN/TC 121 “Welding” the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2007, and conflicting national standards shall be withdrawn at the latest by August 2007.

This document supersedes EN 12072:1999.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Endorsement notice

The text of ISO 14343:2002 and ISO 14343:2002/Amd1:2006 have been approved by CEN as a EN ISO 14343:2007 without any modifications.

INTERNATIONAL STANDARD

ISO
14343

First edition
2002-02-15

Welding consumables — Wire electrodes, wires and rods for arc welding of stainless and heat resisting steels — Classification

*Produits consommables pour le soudage — Fils-électrodes, fils d'apport et
baguettes d'apport pour le soudage à l'arc des aciers inoxydables et des
aciers résistant aux températures élevées — Classification*



Reference number
ISO 14343:2002(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 14343 was prepared in collaboration with the International Institute of Welding which has been approved by the ISO Council as an international standardizing body in the field of welding.

Annex A of this International Standard is for information only.

Introduction

It is recognized that there are two somewhat different approaches in the global market to classifying a given stainless steel welding consumable, and that market allows for either or both to be used, to suit a particular market need. One is termed the “Nominal Composition” approach, which uses designators that indicate the principal alloying elements at their nominal levels, in a particular sequence, sometimes followed by chemical element symbols to indicate compositional modifications to the original grade. The other is termed the “Alloy Type” approach, which uses tradition-based three or four digit designations for certain original grades, sometimes followed by one or more chemical element symbols which indicate compositional modifications from the original. In both approaches, classification is based upon the chemical composition of the product. In many cases a given product can be classified using both approaches, because the composition ranges, although slightly different, overlap to a considerable extent, in the two approaches.

Application of either type of classification designation (or both where suitable) identifies a product as classified according to this International Standard. Many, but not all, commercial products addressed by this International Standard can be classified using both approaches, and suitable products may be so marked. The classification according to system A is mainly based on EN 12072. The classification according to system B is mainly based upon standards used around the Pacific Rim.

For stainless steel welding consumables, there is no unique relationship between the product form (wire electrode, wire or rod) and the welding process used (gas-shielded metal arc welding, gas tungsten arc welding, plasma arc welding or submerged arc welding). For this reason, the wire electrodes, wires or rods may be classified on the basis of any of the above product forms and can be used, as appropriate, for more than one of the above processes.

Welding consumables — Wire electrodes, wires and rods for arc welding of stainless and heat resisting steels — Classification

1 Scope

This International Standard specifies requirements for classification of wire electrodes, wires and rods for gas-shielded metal arc welding, gas tungsten arc welding, plasma arc welding, submerged arc welding and laser beam welding of stainless and heat resisting steels. The classification of the wire electrodes, wires and rods is based upon their chemical composition.

This document is a combined standard providing for classification utilizing a system based upon classification according to nominal composition or utilizing a system based upon classification according to alloy type.

- a) Paragraphs and table entries which carry the label “classification according to nominal composition”, or which are identified by “ISO 14343-A”, are applicable only to products classified to that system.
- b) Paragraphs and table entries which carry the label “classification according to alloy type”, or which are identified by “ISO 14343-B”, are applicable only to products classified to that system.
- c) Paragraphs and table entries which carry neither label are applicable to products classified according to either or both systems.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 31-0:1992, *Quantities and units — Part 0: General principles*

ISO 544, *Welding consumables — Technical delivery conditions for welding filler metals — Type of product, dimensions, tolerances and markings*

ISO 864, *Arc welding — Solid and tubular cored wires which deposit carbon and carbon manganese steel — Dimensions of wires, spools, rims and coils*

ISO 14344, *Welding and allied processes — Flux and gas shielded electrical welding processes — Procurement guidelines for consumables*

3 Terms and definitions

For the purposes of this International Standard, the following terms and definitions apply.

3.1

rod

form of welding filler metal, normally packaged in straight lengths, that does not conduct the welding current, for gas tungsten arc and plasma arc welding

3.2

wire

form of welding filler metal, normally packaged as coils, spools or drums, that does not conduct the welding current, for gas tungsten arc, plasma arc welding and laser beam welding

3.3

wire electrode

form of welding filler metal, normally packaged as coils, spools or drums, that becomes part of the welding circuit through which electrical current is conducted, and that terminates at the arc, for gas-shielded metal arc and submerged arc welding

4 Classification

A wire electrode, wire or rod shall be classified according to its chemical composition as listed in Table 1. The classification is divided into two parts.

- a) The first part gives a symbol indicating the product/process to be identified.
- b) The second part gives a symbol indicating the chemical composition of the wire electrode, wire or rod.

4.1 Symbol for the product/process

ISO 14343-A — Classification according to nominal ISO 14343-B — Classification according to alloy type composition

The symbol for the wire electrode, wire or rod used in the arc welding process is the letter G (gas-shielded metal arc welding), W (gas tungsten arc welding), P (plasma arc welding), S (submerged arc welding) or L (laser beam welding) placed at the beginning of the designation.

No symbol is used to indicate the welding process. The symbol for solid stainless and heat resisting steel wires for use in all welding processes shall be the letters "SS". The initial "S" indicates solid wire as distinguished from covered electrodes or from tubular cored wires. The second "S" indicates that the alloy system is stainless or heat resisting steel.

4.2 Symbol for the chemical composition

The symbol in Table 1 indicates the chemical composition of the wire electrode, wire or rod determined under conditions given in clause 6.

5 Properties of the all-weld metal

Properties of the all-weld metal are not part of the classification.

NOTE 1 The influence of the shielding gas or flux on the chemical composition of the all-weld metal has to be considered. Differences between the chemical composition of the all-weld metal and the wire electrode, wire or rod may occur.

NOTE 2 Proof and tensile strength of the weld metal made by a consumable listed in Table 1 is expected to comply with the minimum requirements in annex A. Elongation and impact properties of the weld metal may deviate from the minimum values specified for the corresponding parent metal as a result of variations in the microstructure.

NOTE 3 Table A.1 lists expected minimum tensile properties of weld metal.

6 Chemical analysis

Chemical analysis shall be performed on specimens of the product. Any analytical technique may be used, but in case of dispute reference shall be made to established published methods.

7 Technical delivery conditions

Technical delivery conditions shall meet the requirements of ISO 544, ISO 864 and ISO 14344.

8 Examples of designation

- a) A wire electrode for gas-shielded metal arc welding, also applicable to submerged arc welding, has a chemical composition within the limits for the alloy symbol 20 10 3 and within the limits for the alloy symbol 308Mo of Table 1.

The designation will be:

Classification according to nominal composition	Classification according to alloy type
ISO 14343-A - G 20 10 3 and/or S 20 10 3	ISO 14343-B - SS308Mo

- b) A rod for gas tungsten arc welding has a chemical composition within the limits for the alloy symbol 20 10 3 and within the limits for the alloy symbol 308Mo of Table 1.

The designation will be:

Classification according to nominal composition	Classification according to alloy type
ISO 14343-A - W 20 10 3	ISO 14343-B - SS308Mo

- c) A wire electrode for gas-shielded metal arc welding has a chemical composition within the limits for the alloy symbol 19 12 3 L Si and within the limits for alloy symbol 316LSi of Table 1.

The designation will be:

Classification according to nominal composition	Classification according to alloy type
ISO 14343-A - G 19 12 3 L Si	ISO 14343-B - SS316LSi

Where, in all three examples,

Classification according to nominal composition	Classification according to alloy type
ISO 14343-A = International Standard number, with classification according to the system A	ISO 14343-B = International Standard number, with classification according to the system B
G, S, W = product/process symbol (see 4.1)	SS = product/process symbol (see 4.1)
20 10 3, 19 12 3 L Si = chemical composition of product (see Table 1).	308Mo, 316LSi = chemical composition of product (see Table 1).

Table 1 — Chemical composition requirements

[illegible]

Austenitic types					0,03	0,03	19,5 to	9,0 to	0,75	—	0,75	—	—
	308	0,08	0,65	1,0 to			<u>22,0</u>	11,0					
				2,5	0,03	0,03	19,5 to	9,0 to	0,75	—	0,75	—	—
	308Si	0,08	0,65 to	1,0 to			<u>22,0</u>	11,0					
			1,00	2,5	0,03	0,02	19,0 to	9,0 to	0,3	—	0,3	—	—
19 9 L	(308L)	0,03	0,65	1,0 to			<u>21,0</u>	11,0					
				2,5	0,03	0,03	19,5 to	9,0 to	0,75	—	0,75	—	—
(19 9 L)	308L	0,03	0,65	1,0 to			<u>22,0</u>	11,0					
				2,5	0,03	0,02	19,0 to	9,0 to	0,3	—	0,3	—	—
							<u>21,0</u>	11,0	0,75	—	0,75	—	—
19 9 L Si	(308LSi)	0,03	0,65 to	1,0 to			19,5 to	9,0 to					
			<u>1,2</u>	2,5	0,03	0,03	<u>22,0</u>	11,0	0,3	—	0,3	10 × C	—
(19 9 L Si)	308LSi	0,03	0,65 to	1,0 to			19,0 to	9,0 to				to 1,0	
			1,00	2,5	0,03	0,02	<u>21,0</u>	11,0	0,75	—	0,75	10 × C	—
19 9 Nb	(347)	0,08	0,65	1,0 to			19,0 to	9,0 to				to 1,0	
				2,5	0,03	0,03	<u>21,5</u>	11,0	0,3	—	0,3	10 × C	—
(19 9 Nb)	347	0,08	0,65	1,0 to			<u>21,0</u>	11,0				to 1,0	
				2,5	0,03	0,03	19,0 to	9,0 to	0,75	—	0,75	10 × C	—
19 9 Nb Si	(347Si)	0,08	0,65 to	1,0 to			<u>21,5</u>	11,0				to 1,0	
			<u>1,2</u>	2,5	0,03	0,03	19,0 to	9,0 to	0,75	—	0,75	10 × C	—
(19 9 Nb Si)	347Si	0,08	0,65 to	1,0 to			<u>21,5</u>	<u>11,0</u>				to 1,0	
			1,00	2,5	0,03	0,03	18,0 to	11,0 to	2,0 to	—	0,75	—	—
	347L	0,03	0,65	1,0 to			20,0	14,0	3,0				
				2,5									
	316	0,08	0,65	1,0 to									
				2,5									

Table 1 (continued)

Alloy designation ^a for classification according to		Chemical composition, % (m/m) ^{b,c}											
Nominal composition ^d	Alloy Type	C	Si	Mn	P	S	Cr	Ni	Mo	N	Cu	Nb ^e	Other
ISO 14343-A	ISO 14343-B												
	316Si	0,08	0,65 to 1,00	1,0 to 2,5	0,03	0,03	18,0 to 20,0	11,0 to 14,0	2,0 to 3,0	—	0,75	—	—
19 12 3 L	(316L)	0,03	0,65	1,0 to 2,5	0,03	0,02	18,0 to 20,0	11,0 to 14,0	2,5 to 3,0	—	0,3	—	—
(19 12 3 L)	316L	0,03	0,65	1,0 to 2,5	0,03	0,03	18,0 to 20,0	11,0 to 14,0	2,0 to 3,0	—	0,75	—	—
19 12 3 L Si	(316LSi)	0,03	0,65 to 1,2	1,0 to 2,5	0,03	0,02	18,0 to 20,0	11,0 to 14,0	2,5 to 3,0	—	0,3	—	—
(19 12 3 L Si)	316LSi	0,03	0,65 to 1,00	1,0 to 2,5	0,03	0,03	18,0 to 20,0	11,0 to 14,0	2,0 to 3,0	—	0,75	—	—
	316LCu	0,03	0,65	1,0 to 2,5	0,03	0,03	18,0 to 20,0	11,0 to 14,0	2,0 to 3,0	—	1,0 to 2,5	—	—
19 12 3 Nb	(318)	0,08	0,65	1,0 to 2,5	0,03	0,02	18,0 to 20,0	11,0 to 14,0	2,5 to 3,0	—	0,3	10 × C to 1,0	—
(19 12 3 Nb)	318	0,08	0,65	1,0 to 2,5	0,03	0,03	18,0 to 20,0	11,0 to 14,0	2,0 to 3,0	—	0,75	8 × C to 1,0	—
	318L	0,03	0,65	1,0 to 2,5	0,03	0,03	18,0 to 20,0	11,0 to 14,0	2,0 to 3,0	—	0,75	8 × C to 1,0	—
19 12 3 Nb Si		0,08	0,65 to 1,2	1,0 to 2,5	0,03	0,02	18,0 to 20,0	11,0 to 14,0	2,5 to 3,0	—	0,3	10 × C to 1,0	—
	317	0,08	0,65	1,0 to 2,5	0,03	0,03	18,5 to 20,5	13,0 to 15,0	3,0 to 4,0	—	0,75	—	—
(18 15 3 L)	317L	0,03	0,65	1,0 to 2,5	0,03	0,03	18,5 to 20,5	13,0 to 15,0	3,0 to 4,0	—	0,75	—	—
321		0,08	0,65	1,0 to 2,5	0,03	0,03	18,5 to 20,5	9,0 to 10,5	0,75	—	0,75	—	Ti 9 × C to 1,0
Ferritic-austenitic types, sometimes referred to as austenitic-ferritic types													
22 9 3 N L	(2209)	0,03	1,0	2,5	0,03	0,02	21,0 to 24,0	7,0 to 10,0	2,5 to 4,0	0,10 to 0,20	0,3	—	—
(22 9 3 N L)	2209	0,03	0,90	0,5 to 2,0	0,03	0,03	21,5 to 23,5	7,5 to 9,5	2,5 to 3,5	0,08 to 0,20	0,75	—	—
25 7 2 L		0,03	1,0	2,5	0,03	0,02	24,0 to 27,0	6,0 to 8,0	1,5 to 2,5	—	0,3	—	—
25 9 3 Cu N L		0,03	1,0	2,5	0,03	0,02	24,0 to 27,0	8,0 to 11,0	2,5 to 4,0	0,10 to 0,20	1,5 to 2,5	—	—
25 9 4 N L		0,03	1,0	2,5	0,03	0,02	24,0 to 27,0	8,0 to 10,5	2,5 to 4,5	0,20 to 0,30	1,5	—	W 1,0
Fully austenitic types^f													
18 15 3 L ^f	(317L) ^f	0,03	1,0	1,0 to 4,0	0,03	0,02	17,0 to 20,0	13,0 to 16,0	2,5 to 4,0	—	0,3	—	—
18 16 5 N L ^f		0,03	1,0	1,0 to 4,0	0,03	0,02	17,0 to 20,0	16,0 to 19,0	3,5 to 5,0	0,10 to 0,20	0,3	—	—
19 13 4 L ^f	(317L) ^f	0,03	1,0	1,0 to 5,0	0,03	0,02	17,0 to 20,0	12,0 to 15,0	3,0 to 4,5	—	0,3	—	—
19 13 4 N L ^f		0,03	1,0	1,0 to 5,0	0,03	0,02	17,0 to 20,0	12,0 to 15,0	3,0 to 4,5	0,10 to 0,20	0,3	—	—
20 25 5 Cu L ^f	(385) ^f	0,03	1,0	1,0 to 4,0	0,03	0,02	19,0 to 22,0	24,0 to 27,0	4,0 to 6,0	—	1,0 to 2,0	—	—
(20 25 5 Cu L) ^f	385 ^f	0,025	0,50	1,0 to 2,5	0,02	0,03	19,5 to 21,5	24,0 to 26,0	4,2 to 5,2	—	1,2 to 2,0	—	—
20 25 5 Cu N L ^f		0,03	1,0	1,0 to 4,0	0,03	0,02	19,0 to 22,0	24,0 to 27,0	4,0 to 6,0	0,10 to 0,20	1,0 to 2,0	—	—

Table 1 (continued)

Alloy designation ^a for classification according to		Chemical composition, % (m/m) ^{b,c}											
Nominal composition ^d	Alloy Type	C	Si	Mn	P	S	Cr	Ni	Mo	N	Cu	Nb ^e	Other
ISO 14343-A	ISO 14343-B												
20 16 3 Mn L ^f		0,03	1,0	5,0 to 9,0	0,03	0,02	19,0 to 22,0	15,0 to 18,0	2,5 to 4,5	—	0,3	—	—
20 16 3 Mn N L ^f		0,03	1,0	5,0 to 9,0	0,03	0,02	19,0 to 22,0	15,0 to 18,0	2,5 to 4,5	0,10 to 0,20	0,3	—	—
25 22 2 N L ^f		0,03	1,0	3,5 to 6,5	0,03	0,02	24,0 to 27,0	21,0 to 24,0	1,5 to 3,0	0,10 to 0,20	0,3	—	—
27 31 4 Cu L ^f	(383) ^f	0,03	1,0	1,0 to 3,0	0,03	0,02	26,0 to 29,0	30,0 to 33,0	3,0 to 4,5	—	0,7 to 1,5	—	—
(27 31 4 Cu L) ^f	383 ^f	0,025	0,50	1,0 to 2,5	0,02	0,03	26,5 to 28,5	30,0 to 33,0	3,2 to 4,2	—	0,7 to 1,5	—	—
	320 ^f	0,07	0,60	2,5	0,03	0,03	19,0 to 21,0	32,0 to 36,0	2,0 to 3,0	—	3,0 to 4,0	8 × C to 1,0	—
	320LR ^f	0,025	0,15	1,5 to 2,0	0,015	0,02	19,0 to 21,0	32,0 to 36,0	2,0 to 3,0	—	3,0 to 4,0	8 × C to 0,40	—
Special types — Often used for dissimilar metal joining													
	307 ^f	0,04 to 0,14	0,65	3,3 to 4,8	0,03	0,03	19,5 to 22,0	8,0 to 10,7	0,5 to 1,5	—	0,75	—	—
18 8 Mn ^f		0,20	1,2	5,0 to 8,0	0,03	0,03	17,0 to 20,0	7,0 to 10,0	0,3	—	0,3	—	—
20 10 3	(308Mo)	0,12	1,0	1,0 to 2,5	0,03	0,02	18,0 to 21,0	8,0 to 12,0	1,5 to 3,5	—	0,3	—	—
(20 10 3)	308Mo	0,08	0,65	1,0 to 2,5	0,03	0,03	18,0 to 21,0	9,0 to 12,0	2,0 to 3,0	—	0,75	—	—
	308LMo	0,03	0,65	1,0 to 2,5	0,03	0,03	18,0 to 21,0	9,0 to 12,0	2,0 to 3,0	—	0,75	—	—
23 12 L	(309L)	0,03	0,65	1,0 to 2,5	0,03	0,02	22,0 to 25,0	11,0 to 14,0	0,3	—	0,3	—	—
(23 12 L)	309L	0,03	0,65	1,0 to 2,5	0,03	0,03	23,0 to 25,0	12,0 to 14,0	0,75	—	0,75	—	—
23 12 L Si	(309LSi)	0,03	0,65 to 1,2	1,0 to 2,5	0,03	0,02	22,0 to 25,0	11,0 to 14,0	0,3	—	0,3	—	—
(23 12 L Si)	309LSi	0,03	0,65 to 1,00	1,0 to 2,5	0,03	0,03	23,0 to 25,0	12,0 to 14,0	0,75	—	0,75	—	—
23 12 Nb		0,08	1,0	1,0 to 2,5	0,03	0,02	22,0 to 25,0	11,0 to 14,0	0,3	—	0,3	10 × C to 1,0	—
	309LNb	0,03	0,65	1,0 to 2,5	0,03	0,03	23,0 to 25,0	12,0 to 14,0	0,75	—	0,75	10 × C to 1,0	—
	309Mo	0,12	0,65	1,0 to 2,5	0,03	0,03	23,0 to 25,0	12,0 to 14,0	2,0 to 3,0	—	0,75	—	—
23 12 2 L	(309LMo)	0,03	1,0	1,0 to 2,5	0,03	0,02	21,0 to 25,0	11,0 to 15,5	2,0 to 3,5	—	0,3	—	—
(23 12 2 L)	309LMo	0,03	0,65	1,0 to 2,5	0,03	0,03	23,0 to 25,0	12,0 to 14,0	2,0 to 3,0	—	0,75	—	—
29 9	(312)	0,15	1,0	1,0 to 2,5	0,03	0,02	28,0 to 32,0	8,0 to 12,0	0,3	—	0,3	—	—
(29 9)	312	0,15	0,65	1,0 to 2,5	0,03	0,03	28,0 to 32,0	8,0 to 10,5	0,75	—	0,75	—	—
Heat resisting types													
16 8 2	(16-8-2)	0,10	1,0	1,0 to 2,5	0,03	0,02	14,5 to 16,5	7,5 to 9,5	1,0 to 2,5	—	0,3	—	—
(16 8 2)	16-8-2	0,10	0,65	1,0 to 2,5	0,03	0,03	14,5 to 16,5	7,5 to 9,5	1,0 to 2,0	—	0,75	—	—
19 9 H	(19-10H)	0,04 to 0,08	1,0	1,0 to 2,5	0,03	0,02	18,0 to 21,0	9,0 to 11,0	0,3	—	0,3	—	—

Table 1 (continued)

Alloy designation ^a for classification according to		Chemical composition, % (m/m) ^{b,c}											
Nominal composition ^d	Alloy Type	C	Si	Mn	P	S	Cr	Ni	Mo	N	Cu	Nb ^e	Other
ISO 14343-A	ISO 14343-B												
(19 9 H)	19-10H	0,04 to 0,08	0,65	1,0 to 2,0	0,03	0,03	18,5 to 20,0	9,0 to 11,0	0,25	—	0,75	0,05	Ti 0,05
(19 9 H)	308H	0,04 to 0,08	0,65	1,0 to 2,5	0,03	0,03	19,5 to 22,0	9,0 to 11,0	0,50	—	0,75	—	—
19 12 3 H	(316H)	0,04 to 0,08	1,0	1,0 to 2,5	0,03	0,02	18,0 to 20,0	11,0 to 14,0	2,0 to 3,0	—	0,3	—	—
(19 12 3 H)	316H	0,04 to 0,08	0,65	1,0 to 2,5	0,03	0,03	18,0 to 20,0	11,0 to 14,0	2,0 to 3,0	—	0,75	—	—
22 12 H	(309)	0,04 to 0,15	2,0	1,0 to 2,5	0,03	0,02	21,0 to 24,0	11,0 to 14,0	0,3	—	0,3	—	—
(22 12 H)	309	0,12	0,65	1,0 to 2,5	0,03	0,03	23,0 to 25,0	12,0 to 14,0	0,75	—	0,75	—	—
	309Si	0,12	0,65 to 1,00	1,0 to 2,5	0,03	0,03	23,0 to 25,0	12,0 to 14,0	0,75	—	0,75	—	—
25 4		0,15	2,0	1,0 to 2,5	0,03	0,02	24,0 to 27,0	4,0 to 6,0	0,3	—	0,3	—	—
25 20 ^f	(310) ^f	0,08 to 0,15	2,0	1,0 to 2,5	0,03	0,02	24,0 to 27,0	18,0 to 22,0	0,3	—	0,3	—	—
(25 20) ^f	310 ^f	0,08 to 0,15	0,65	1,0 to 2,5	0,03	0,03	25,0 to 28,0	20,0 to 22,5	0,75	—	0,75	—	—
	310S ^f	0,08	0,65	1,0 to 2,5	0,03	0,03	25,0 to 28,0	20,0 to 22,5	0,75	—	0,75	—	—
	310L ^f	0,03	0,65	1,0 to 2,5	0,03	0,03	25,0 to 28,0	20,0 to 22,5	0,75	—	0,75	—	—
25 20 H ^f		0,35 to 0,45	2,0	1,0 to 2,5	0,03	0,02	24,0 to 27,0	18,0 to 22,0	0,3	—	0,3	—	—
25 20 Mn ^f		0,08 to 0,15	2,0	2,5 to 5,0	0,03	0,02	24,0 to 27,0	18,0 to 22,0	0,3	—	0,3	—	—
18 36 H ^f	(330)	0,18 to 0,25	0,4 to 2,0	1,0 to 2,5	0,03	0,02	15,0 to 19,0	33,0 to 37,0	0,3	—	0,3	—	—
(18 36 H) ^f	330	0,18 to 0,25	0,65	1,0 to 2,5	0,03	0,03	15,0 to 17,0	34,0 to 37,0	0,75	—	0,75	—	—
Precipitation hardening type													
	630	0,05	0,75	0,25 to 0,75	0,03	0,03	16,00 to 16,75	4,5 to 5,0	0,75	—	3,25 to 4,00	0,15 to 0,30	—

a A designation in parentheses, e.g., (308L) or (19 9 L) indicates a near match in the other designation system, but not an exact match. The correct designation for a given composition range is the one not in parentheses. A given product may, by having a more restricted chemical composition which fulfills both sets of designation requirements, be assigned both designations independently.

b Single values shown in the table are maximum values. Two values shown indicate minimum and maximum limits for a range.

c The results shall be rounded to the same number of significant figures as in the specified value using the rules in accordance with annex B, Rule A of ISO 31-0:1992.

d Wire electrodes not listed in the table shall be symbolized similarly and prefixed by the letter Z.

e Up to 20% of the amount of Nb can be replaced by Ta.

f The all-weld metal is in most cases fully austenitic and therefore can be susceptible to microfissuring or hot cracking. The occurrence of fissuring/cracking is reduced by increasing the weld metal manganese level and in recognition of this the manganese range is extended for a number of grades.

Annex A

(informative)

Expected minimum tensile properties of all-weld metal

Table A.1 — Expected minimum tensile properties of all-weld metal

Alloy symbol		Mechanical property			Postweld heat treatment
Classification according to nominal composition ISO 14343-A	Classification according to alloy type ISO 14343-B	Proof strength $R_{p0,2}$ N/mm ²	Tensile strength R_m N/mm ²	Elongation ^a %	
13 ^c 13 L 13 4 17	409	180	380	14	none
	409Nb	250	450	15	b
	410 ^b	250	450	15	c or b
		250	450	15	c
	410NiMo	500	750	15	d
	420	250	450	15	c
	430	300	450	15	e
	430Nb	250	450	15	e
18LNb	430LNb	220	410	15	none
19 9 L 19 9 L Si 19 9 Nb 19 9 Nb Si 19 12 3 L 19 12 3 L Si 19 12 3 Nb 19 12 3 Nb Si 18 15 3 L	308	350	550	30	none
	308Si	350	550	30	none
	308L	320	510	30	none
	308LSi	320	510	30	none
	347	350	550	25	none
	347Si	350	550	25	none
	347L	320	510	25	none
	316	320	510	25	none
	316Si	320	510	25	none
	316L	320	510	25	none
	316LSi	320	510	25	none
	316LCu	320	510	25	none
	318	350	550	25	none
	318L	320	510	25	none
		350	550	25	none
	317	350	550	25	none
	317L	300	480	25	none
	321	350	550	25	none
22 9 3 N L	2209	450	550	20	none
25 7 2 L		500	700	15	none
25 9 3 Cu N L		550	620	18	none
25 9 4 N L		550	620	18	none

Table A.1 (continued)

Alloy symbol		Mechanical property			Postweld heat treatment
Classification according to nominal composition ISO 14343-A	Classification according to alloy type	Proof strength	Tensile strength	Elongation ^a	
18 15 3 L 18 16 5 N L 19 13 4 L 19 13 4 N L 20 25 5 Cu L 20 25 5 Cu N L 20 16 3 Mn L 20 16 3 Mn N L 25 22 2 N L 27 31 4 Cu L	ISO 14343-B 385	R _{p0,2} N/mm ² 300 300 350 350 320 320 320 320	R _m N/mm ² 480 480 550 550 510 510 510 510	% 25 25 25 25 25 25 25 25	none none none none none none none none
18 8 Mn 20 10 3 23 12 L 23 12 L Si 23 12 Nb 23 12 2 L 29 9	383 320 320LR 307 308Mo 308LMo 309L 309LSi	320 240 320 300 350 350 400 320 320 320	510 500 550 520 590 500 620 510 510 510	25 25 25 25 25 20 30 25 25	none none none none none none none none none
16 8 2 19 9 H 19 12 3 H 22 12 H 25 4 25 20 25 20 Mn 25 20 H 18 36 H	309LNb 309Mo 309LMo 312 16-8-2 19-10H 308H 316H 309 309Si 310 310S	320 350 350 450 320 350 350 350 350 350 450 350 350	510 550 550 650 510 550 550 550 550 550 650 550 550	25 25 25 15 25 30 30 25 25 25 15 20	none none none none none none none none none none none none
	310L	320 350 350 350	510 550 550 550	20 20 10 ^f 10 ^f	none none none none
	330	350	550		none
	630	725	930	5	g

^a Gauge length is equal to five times the specimen diameter.

^b 730 °C /760 °C for 1 h, furnace cooling down to 600 °C, then air cooling.

- c 840 °C /870 °C for 2 h, furnace cooling down to 600 °C, then air cooling.
 - d 580 °C /620 °C for 2 h, air cooling.
 - e 760 °C /790 °C for 2 h, furnace cooling down to 600 °C, then air cooling.
 - f These wire electrodes deposit high carbon weld metal for service at high temperatures. Room temperature elongation has little relevance to such applications.
- NOTE Weld metal may have elongation lower than that of the parent metal.
- g 1 025 °C /1 050 °C for 1 h, air cool to ambient, then 610 °C /630 °C for 4 h, air cool.

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001. Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager. Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553. Email: copyright@bsi-global.com.

BSI

389 Chiswick High Road
London
W4 4AL